



www.glasbord.com

# TECHNICAL DATA 65020

Rev. 13 06/09

## FSI

### SMOOTH WALL PANEL CLASS A FIRE RATING AS TESTED PER ASTM E-84

#### Product

Glasbord-FSI with Surfaseal is made of fiberglass reinforced plastic. It is a durable, flexible building material and will not mold, mildew, rot, or corrode. It exhibits excellent resistance to mild chemicals and moisture. The panel has a Class A (1) rating for flame spread and smoke development.

#### Surfaseal Finish

Surfaseal is a unique surface treatment that, when compared to ordinary fp, exhibits up to ten times the cleanability, six times the stain resistance, and twice the abrasion resistance.

#### Purpose

Glasbord-FSI smooth panels are designed for interior wall finishes where a Class A, sanitary, easy to clean panel is desired. Smooth panels will withstand moderate abuse. For high abuse resistance, embossed panels are recommended.

PHYSICAL PROPERTIES: TABLE 1

PROPERTY	TYPICAL VALUE		TEST METHOD
	0.075"	1.9 mm	
Flexural Strength	14 x 10 <sup>3</sup> psi	97 MPa	ASTM D790
Flexural Modulus	0.65 x 10 <sup>6</sup> psi	4482 MPa	ASTM D790
Tensile Strength	7 x 10 <sup>3</sup> psi	48 MPa	ASTM D638
Tensile Modulus	0.95 x 10 <sup>6</sup> psi	6550 MPa	ASTM D638
Barcol Hardness	50	50	ASTM D2583
Izod Impact Strength	11 ft-lb/in notched	0.58 J/mm	ASTM D256
Gardner Impact Strength	35 in-lbs	4 J	ASTM D5420
Coefficient of Linear Thermal Expansion	1.4 x 10 <sup>-5</sup> in/in•°F	25 µm/m•°C	ASTM D696
Water Absorption	0.38%/24 hrs @77°F	0.38%/24 hrs @25°C	ASTM D570
Specific Gravity	1.8	1.8	ASTM D792
R Value	0.19 hr•ft <sup>2</sup> •°F/Btu	0.039 hr•m <sup>2</sup> •°C/kcal	ASTM D177
Surface Burning Characteristics	Class A	Class A	ASTM E84
Taber Abrasion Resistance (cs-17 wheels, 1000 g. wt., 25 cycles)	0.005% max wt loss	0.005% max wt loss	Taber Abrader

DESIGN DATA: TABLE 2

PART NUMBER IDENTIFIER	AVAILABLE COLORS	SIZE	FINISH	NOMINAL THICKNESS
FSI	85 white	4' x 8', 9', 10', 12' (1.2m x 2.4m, 2.7m, 3.0m, 3.7m)	smooth	0.075" (1.9 mm)

Other lengths, widths, and colors available by quotation.

## SPECIFICATIONS

These panels are manufactured by a continuous laminating process in lengths as required.

## COMPOSITION

1. **Reinforcement:** Random chopped fiberglass roving.
2. **Resin mix:** Modified polyester copolymer and inorganic fillers and pigments.

## FINISHED PANEL QUALITY

1. Panels shall have a wear side with a smooth finish. Color shall be uniform throughout, as specified. Other colors can be manufactured. The backside shall be smooth. Backside imperfections that do not affect functional properties are not cause for rejection.
2. Physical properties shall be as set forth in Table 1.
3. Product quality standards and tolerances for panel weight and thickness shall be as set forth in Crane Composites' Quality Control Procedures/Standards which are available on request.
4. Dimensions shall be as specified on purchase order, subject to the following tolerances:  
**Width:**  $\pm 1/8"$  (3.2 mm)  
**Length:**  $\pm 1/8"$  (3.2 mm) up to 12' (3.7 m)  
**Squareness:** not more than  $1/8"$  (3.2 mm) out of square.
5. Panels shall be installed in accordance with manufacturer's guidelines as set forth in the Glasbord "Installation Guide."
6. Bulk Coil Policy #6207 applies for coils for lamination.

## CERTIFICATION

- A. Meets USDA/FSIS requirements.
- B. Meets minimum requirements of major model building codes for Class A (1) interior wall and ceiling finishes. Flame spread less than 25, smoke developed 450 or less (per ASTM E-84).
- C. Frp does not support mold or mildew (per ASTM D3273 and ASTM D3274).
- D. Meets FMVSS 302 Requirements.

## FABRICATING RECOMMENDATIONS

**Note:** Protect your eyes with goggles; cover your nose and mouth with a filter mask when cutting Glasbord panels.

**Hand fabricating:** Drilling—High speed drill bit (60° cutting angle, with 12°-15° clearance) or hole saw.

**Stapling:** Standard pneumatic stapler.

**Cutting:** Sheet metal shears or circular saw with reinforced carbondum or carbide-tipped blade.

**Production fabricating:** Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" [0.05 mm] clearance) or sawed. For irregular cuts, use die punch or band saw.

## STORAGE

All Crane Composites products should be stored indoors.

## SERVICEABLE TEMPERATURE RANGE

Panels will perform in temperatures from -40°F (-40°C) to 130°F (54°C). For use in environments beyond this range, contact Crane Composites for recommendations.

## PRODUCT LIMITATIONS

**Near heat source:** Glasbord panel products may discolor when installed near a heat source which radiates temperatures exceeding 130°F (55°C) such as cookers, ovens, and deep fryers.

**Uneven surface:** Installation over uneven concrete block walls may result in areas of delamination and bulging.

## KEMLITE TESTING

**Cleanability test:** When Glasbord with Surfaseal and an ordinary frp panel are heavily soiled, the Glasbord panel exhibits up to 10 times more cleanability per MacBeth Computer Colorimeter.

**Stain resistance test:** Prolonged direct contact to concentrated ammonia-based cleaner exhibited no color change per MacBeth Computer Colorimeter.

## NOTICE

Panels will provide a clean, aesthetically-pleasing finished installation. However, by nature, fiberglass reinforced plastic paneling may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected on-site prior to installation. If any portion of material will not provide an acceptable appearance, Crane Composites should be notified at once. Upon verification of unacceptability, that portion of material will be replaced by Crane Composites. Crane Composites' sole responsibility is for the replacement of defective material but not for labor or other handling or installation expenses.

### FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS

The numerical flame spread and smoke development ratings are not intended to reflect hazards presented by Crane Composites products or any other material under actual fire conditions. These ratings are determined by small-scale tests conducted by Underwriters Laboratories and other independent testing facilities using the American Society for Testing and Materials E-84 test standard (commonly referred to as the "Tunnel Test"). CRANE COMPOSITES PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, frp may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction and occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated interior finish and fire suppression system necessary for a specific installation.

We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents.

### Additional Information Available:

- #6211 Installation Guide
- CSI Specifications
- #6220 Accessories Tech Data



1•800•435•0080 ph.  
1•815•467•8600 ph.  
1•815•467•8666 fax  
www.glasbord.com

Glasbord and Surfaseal are  
registered trademarks of Crane Composites, Inc.



Form 65020 Rev. 13 (5166)