



Glasbord® Embossed Wall Panels | FX

Class A Fire-Rating per ASTM E-84

Product

Fire-X Glasbord with Surfaseal is made of fiberglass reinforced plastic. Fire-X Glasbord is a durable, flexible building material and will not mold, mildew, rot or corrode. It exhibits excellent resistance to mild chemicals and moisture. The panel has a Class A rating for flame spread and smoke development when tested per ASTM E-84.

Purpose

Fire-X Glasbord with Surfaseal embossed panels are designed for interior wall finishes where a Class A, sanitary, easy-to-clean panel is desired.

Surfaseal® Finish

Surfaseal is a unique surface treatment that, when compared to ordinary FRP, exhibits up to ten times cleanability, six times the stain resistance and twice the abrasion resistance.

Table One: Physical Properties

| Typical Values | | | | | |
|---|---|---|---|---|--------------|
| Property | FX 0.06" | FX 0.09" | FX 0.10" | FX 0.12" | Test Method |
| Flexural Strength | 12 x 10 ³ psi 83 MPa | 13.6 x 10 ³ psi 94 MPa | 14.1 x 10 ³ psi 97 MPa | 14.6 x 10 ³ psi 101 MPa | ASTM - D790 |
| Flexural Modulus | 0.44 x 10 ⁶ psi 3034 MPa | 0.6 x 10 ⁶ psi 4137 MPa | 0.61 x 10 ⁶ psi 4206 MPa | 0.7 x 10 ⁶ psi 4826 MPa | ASTM - D790 |
| Tensile Strength | 6.1 x 10 ³ psi 42 MPa | 7.1 x 10 ³ psi 49 MPa | 7.4 x 10 ³ psi 51 MPa | 7.5 x 10 ³ psi 52 MPa | ASTM - D638 |
| Tensile Modulus | 0.84 x 10 ⁶ psi 5792 MPa | 0.92 x 10 ⁶ psi 6343 MPa | 0.92 x 10 ⁶ psi 6343 MPa | 0.94 x 10 ⁶ psi 6481 MPa | ASTM - D638 |
| Barcol Hardness | 30 | 40 | 40 | 40 | ASTM - D2583 |
| Izod Impact | 10.0 ft-lb/in notched 0.53 J/mm | 12.0 ft-lb/in notched 0.64 J/mm | 12.0 ft-lb/in notched 0.64 J/mm | 14.0 ft-lb/in notched 0.75 J/mm | ASTM - D256 |
| Coefficient of Linear Thermal Expansion | 0.17 x 10 ⁻⁵ in/in/°F 31 µm/m/°C | 0.17 x 10 ⁻⁵ in/in/°F 31 µm/m/°C | 0.17 x 10 ⁻⁵ in/in/°F 31 µm/m/°C | 0.17 x 10 ⁻⁵ in/in/°F 31 µm/m/°C | ASTM - D696 |
| Gardner Impact Strength | 10 in-lb 1.1 J | 45 in-lb 5.1 J | 45 in-lb 5.1 J | 45 in-lb 5.1 J | ASTM - D3029 |
| Water Absorption | 0.35%/24hrs@77°F 25°C | 0.32%/24hrs@77°F 25°C | 0.32%/24hrs@77°F 25°C | 0.32%/24hrs@77°F 25°C | ASTM - D570 |
| R Value | 0.15 hr•ft ² •°F/BTU 0.031 hr•m ² •°C/kcal | 0.23 hr•ft ² •°F/BTU 0.047 hr•m ² •°C/kcal | 0.25 hr•ft ² •°F/BTU 0.051 hr•m ² •°C/kcal | 0.30 hr•ft ² •°F/BTU 0.061 hr•m ² •°C/kcal | ASTM - C114 |
| Surface Burning Characteristics | Class A | Class A | Class A | Class A | ASTM - E84 |
| Taber Abrasion Resistance (cs-17 wheels, 1000g. Wt, 25 cycles) | 0.09%Max Wt. Loss | 0.02%Max Wt. Loss | 0.02%Max Wt. Loss | 0.03%Max Wt. Loss | Taber Test |

Table Two: Physical Properties

| Product Code | Nominal Thickness | Finish | Color | Available Sizes |
|--------------|-------------------|----------|---|--|
| FX | 0.06" 1.5 mm | Embossed | White 85 Beige 70 Ivory 84 | 45" to 50" x 5' to 700' 1.1 m to 1.2 m x 1.5m to 213 m |
| | 0.09" 2.3 mm | | Colonial White 83 Pearl Gray 48 Silver 66 | |
| | 0.10" 2.5 mm | | White 85 | 4' x 8' 4' x 9' 4' x 10' 4' x 12' 1.2 m x 2.4 m 1.2 m x 2.7 m 1.2 m x 3.0 m 1.2 m x 3.7 m |
| | 0.12" 3.0 mm | | | |

Additional lengths, widths and colors available by quotation. 12,000 sq. ft. per product, weight and colors required to manufacture. Orders from different customers may be batched to obtain manufacturing minimums, however lead time may be affected.

SPECIFICATIONS

Crane Composites panels are manufactured by a continuous laminating process in lengths as required.

COMPOSITION

Reinforcement: Random chopped fiberglass.

Resin Mix: Modified polyester copolymer and inorganic fillers and pigments.

FINISHED PANEL QUALITY

1. Panels shall have a wear side with a pebble-like embossed finish. Color shall be uniform throughout, as specified. The backside shall be smooth. Backside imperfections which do not affect functional properties are not cause for rejection.
2. Physical properties shall be as set forth in Table 1.
3. Dimensions shall be as specified on purchase order, subject to the following tolerances:
Width: $\pm 1/8"$ (± 3.2 mm)
Length: $\pm 1/8"$ (± 3.2 mm) up to 12' (3.7 m)
Squareness: $\pm 1/8"$ (3.2 mm) in 48" (1.2 m) of width
4. Product quality standards and tolerances for panel weight and thickness shall be as set forth in Crane Composites' Quality Control Procedures/Standards which are available on request.
5. Panels shall be installed in accordance with manufacturer's guidelines as set forth in the Crane Composites Installation Guide (Form #6876).

CERTIFICATIONS

1. Meets USDA/FSIS requirements
2. Meets FMVSS 302 Requirements
3. FRP does not support mold or mildew (per ASTM D3273 and ASTM D3274)
4. Meets minimum requirements of major model building codes for Class A interior wall and ceiling finishes of flame spread ≤ 25 , smoke developed 450 or less (per ASTM E-84)
5. Crane Composites certifies that Fire-X Glasbord (FX) meets the requirements of ASTM D5319.
Classification Class A - Flame spread 0 to 25, smoke development index of 450 or less per ASTM E 84.
Grade 6: 0.081 to 0.099 in. (2.06 to 2.51mm); 0.090 in. nominal (2.29mm).
Tolerances: Width and Length: $\pm .125$ in (3.175mm) up to and including 12 ft.
Squareness: $\pm .125$ in (3.175mm)
Thickness: $\pm 10\%$ Camber: $\pm .25$ in (6.35mm)
6. Product identified by 2 red and 1 blue threads on the back.
7. Two Translucent Plastic Threads with Fluorescent Pigment Design[®] on the front identifies Fire-X Glasbord
8. Meets Canadian code CAN/ULC-S102 of ≤ 25 flame spread and ≤ 300 smoke developed
9. MEA Approved. MEA 16-85M. VOL. II



FLAME SPREAD AND SMOKE DEVELOPMENT RATINGS

The numerical flame spread and smoke development ratings are not intended to reflect alleged hazards presented by Crane Composites products under actual fire conditions and this product has not been tested by Crane Composites except as set forth below. These ratings are determined by small-scale tests conducted by Underwriters Laboratories and other independent testing facilities using the American Society for Testing and Materials E-84 test standard (commonly referred to as the "Tunnel Test").

CRANE COMPOSITES PROVIDES THESE RATINGS FOR MATERIAL COMPARISON PURPOSES ONLY. Like other organic building materials (e.g. wood), panels made of fiberglass reinforced plastic resins will burn. When ignited, FRP may produce dense smoke very rapidly. All smoke is toxic. Fire safety requires proper design of facilities and fire suppression systems, as well as precautions during construction and occupancy. Local codes, insurance requirements and any special needs of the product user will determine the correct fire-rated interior finish and fire suppression system necessary for a specific installation. We believe all information given is accurate, without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents. www.astm.org/Standards/E84.htm.

FABRICATING RECOMMENDATIONS

Note: Protect your eyes with goggles; cover your nose and mouth with a filter mask; cover exposed skin when cutting CCI panels.

Hand Fabricating: Drilling—High speed drill bit (60° cutting angle, with 12°-15° clearance) or hole saw.

Cutting: Sheet metal shears or circular saw with reinforced carbonundum or carbide-tipped blade.

Production Fabricating: Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" [0.05 mm] clearance) or sawed. For irregular cuts, use die punch or band saw.

Cleaning Instructions: Available from CCI.

STORAGE

All Crane Composites FRP products should be stored indoors.

SERVICEABLE TEMPERATURE RANGE

Panels will perform in temperatures from -40°F (-40°C) to 150°F (66°C). For use in environments beyond this range contact Crane Composites for recommendations.

LIMITATIONS

Near Heat Source: Crane Composites panels may discolor when installed behind or near any heat source which radiates temperatures exceeding 130°F (55°C), such as cookers, ovens, and deep fryers.

Uneven Surface: Installation over uneven concrete block walls may result in areas of delamination and bulging.

CRANE COMPOSITES TESTING

Cleanability Test: When Glasbord with Surfaseal and an ordinary FRP panel are heavily soiled, the Glasbord panel exhibits up to 10 times more cleanability per MacBeth Computer Colorimeter.

Stain Resistance Test: Prolonged direct contact to concentrated ammonia-based cleaner exhibited no color change per MacBeth Color Colorimeter.



NOTICE

Panels will provide a clean, aesthetically-pleasing finished installation. However, by nature, fiberglass reinforced plastic paneling may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected on-site prior to installation. If any portion of material does not provide an acceptable appearance, Crane Composites should be notified at once. Upon verification of unacceptability, that portion of material will be replaced by Crane Composites. Crane Composites' sole responsibility is for the replacement of defective materials but not for labor or other handling or installation expenses.

www.FRP.com | 1.800.435.0080 | 1.815.467.8666 (fax) | salesbp@cranecomposites.com

Crane Composites is the manufacturer of Glasbord, Sequentia, Sanigrid II and a variety of other fiberglass reinforced plastic (FRP) composite wall panels. Inspired by the Kemlite tradition, Crane Composites has over 55 years of experience in Commercial Building Products and is a recognized industry leader in FRP applications.



CRANE Composites

We believe all information given is accurate. It is offered in good faith, but without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents.