



MSDS | Material Safety Data Sheet

Product Identification

Trade Name and Synonyms
Chemical Name and Synonyms
Chemical Family
DOT Hazard Classification

Sanigrid_® Fiberglass Ceiling Grid System Fiberglass Reinforced Plastic (frp) Polymerized Thermoset Polyesters Not Applicable

Composition/Information on Ingredients

The Sanigrid II ceiling system is composed of a mixture of isophthalic polyester resin, inorganic fillers, processing additives, and fiberglass reinforcement. During the manufacturing process, this mixture is cured or hardened into a stable, solid material that is non-hazardous when handled or processed in accordance with good manufacturing and industrial hygiene practices.

Hazards Identification

Threshold Limit Value (TLV)

Primary Route of Entry Effects of Overexposure

Fabricating, cutting, drilling, etc. of frp may produce dust, which should be controlled. Particulate level should not exceed 30M ppcf.

Inhalation of or skin contact with dust.

Exposure to dust in excess of TLV may result in skin or upper respiratory tract irritation. Pre-existing skin or respiratory disorders may cause more susceptibility to these effects.

Physical Data

Boiling Point
Vapor Pressure
Vapor Density
Specific Gravity (water=1)
% Volatile (by volume)
Solubility in Water

Not applicable Not applicable Not applicable 1.6 g/cm³ Not applicable Insoluble

First Aid Measures

Inhalation of Dust

Remove from source of exposure into fresh air. Ensure clear airway. Get medical help.

Prolonged Skin Contact

Remove contaminated clothing. Wash skin with warm water and soap.

Skin cream could be helpful.

Eye Contact Ingestion of DustFlush with running water for 15 minutes or more.

Do not induce vomiting. Get medical help.

Fire and Explosion Data

Flash Point Ignition Temperature Extinguishing Media

Fire Fighting Procedures

Unusual Fire or Explosion Hazards

Decomposition Products

Not Applicable.

Typically 650°F or higher for frp panels.

Water, CO2, dry chemical.

Use media best suited to fire environment. Use water to cool fire-exposed containers and to flush spills from ignition sources. Use

self-contained breathing apparatus for large scale fires.

As with other building materials, combustion will yield toxic materials such as carbon monoxide (CO) and carbon dioxide (CO2, and may also yield aliphatic and aromatic hydrocarbons and halogenated compounds. Under fire conditions only, fumes may contain carbon monoxide and

halogens.

Reactivity Data

This material is stable. Hazardous polymerization will not occur. Organic solvents soften material if allowed to be in contact for a prolonged length of time.

Environmental Information

Transportation Data Special Precautions Most cured polyesters have little or no toxic effect. If curing is incomplete,

there may be residues of toxic peroxides or styrene monomers. No special regulations govern transportation of this product.

Dispose of in accordance with local, provincial, and federal regulations.

Incinerate only at approved disposal sites.

Personal Protection Information

Respiratory Protection

Eye Protection

Skin Protection

Use adequate ventilation to control dust when machining, cutting, drilling, etc. Cover nose and mouth with mask approved by NIOSH/OSHA. Use goggles or safety glasses when machining, cutting, drilling, etc. Have eye washes available.

Wear protective gloves, long pants and long sleeves when machining, cutting, drilling, etc. Wash skin with soap and water after handling. Wash dusty work clothes separately.

a. Bainey

Approved By

Date

