

GENERAL PURPOSE daylighting panels

PRODUCT CODE: ***GP

PRODUCT

General Purpose (GP) translucent and opaque Fiberglass Reinforced Plastic (FRP) panels are produced with general purpose resin combined with random chopped fiberglass for reinforcement.

PURPOSE

General Purpose panels are used where standard weathering characteristics are required. This panel offers light transmission, standard chemical resistance, and is suitable for a variety of applications.

DESIGN PROPERTIES

PRODUCT CODE	TYPE	WEIGHT	COLOR	LIGHT TRANSMISSION	SIZE
XXXGP xxx = PROFILE NUMBER	Translucent	5 oz./ft ² 6 oz./ft ² 8 oz./ft ² 10 oz./ft ²	502 Clear 467 White 405 Snowflake White	40-50% 50-60% 80%	As defined by tooling and approved drawing

Percentages of light transmission shown are nominal values with a tolerance of + or - 5%

Methods of test: Light Transmission per ASTM D1494

*Light Transmission applies to 8 oz/ft² only.

TYPICAL PHYSICAL PROPERTIES

PROPERTY	GP 5oz./ft ²	GP 6oz./ft ²	GP 8oz./ft ²	GP 10oz./ft ²	TEST METHOD
FLEXURAL STRENGTH	20 x 10 ³ psi 138 MPa	25 x 10 ³ psi 172 MPa	30 x 10 ³ psi 207 MPa	33 x 10 ³ psi 228 MPa	ASTM - D638
FLEXURAL MODULUS	0.5 x 10 ³ psi 3447 MPa	0.7 x 10 ³ psi 4826 MPa	0.6 x 10 ³ psi 4137 MPa	0.6 x 10 ³ psi 4137 MPa	ASTM - D638
TENSILE STRENGTH	10 x 10 ³ psi 69 MPa	15 x 10 ³ psi 103 MPa	20 x 10 ³ psi 138 MPa	20 x 10 ³ psi 138 MPa	ASTM - D790
TENSILE MODULUS	1.0 x 10 ³ psi 6895 MPa	1.2 x 10 ³ psi 8274 MPa	1.5 x 10 ³ psi 10,342 MPa	1.6 x 10 ³ psi 11,032 MPa	ASTM - D790
COEFFICIENT OF LINEAR THERMAL EXPANSION	1.6 x 10 ⁻⁵ in/in/°F 29 μm/m/°C	1.6 x 10 ⁻⁵ in/in/°F 29 μm/m/°C	1.6 x 10 ⁻⁵ in/in/°F 29 μm/m/°C	1.6 x 10 ⁻⁵ in/in/°F 29 μm/m/°C	ASTM - D696
AVERAGE BURN RATE	N/A	≤ 2.5 in/min	N/A	≤ 2.5 in/min	ASTM - C1363
ICC COMBUSTIBILITY CLASSIFICATION	N/A	CC2	N/A	CC2	ASTM - C177
SELF IGNITION TEMPERATURE	> 650°F > 343°C	> 650°F > 343°C	> 650°F > 343°C	> 650°F > 343°C	ASTM - D635
FLASH IGNITION TEMPERATURE	> 650°F > 343°C	> 650°F > 343°C	> 650°F > 343°C	> 650°F > 343°C	ASTM - D635

TESTING

Crane Composites panels meet or exceed applicable requirements of the following standards:

1. ASTM D3841, Standard Specification for Glass Fiber Reinforced Polyester Plastic Panels.
2. Code requirements of most state, county and municipal building departments.
3. Crane Composites is a recognized UL90 component manufacturer.

SPECIFICATIONS

Crane Composites, Inc. (CCI) panels are manufactured by a continuous laminating process in lengths as required.

COMPOSITION

Reinforcement: Random chopped fiberglass.

Resin Mix: Polyester/styrene copolymer, inorganic fillers, and pigments.

FINISHED PANEL QUALITY

1. Panels shall have a wear side with a smooth or textured finish. Color shall be uniform throughout as specified. The backside shall be smooth. The backside surface may have some variations which do not affect functional properties and are not cause for rejection.
2. Physical properties shall be as set forth on Page 1.
3. Dimensions shall be as specified on purchase order, subject to the following tolerances:
WIDTH: $\pm 1/8"$ (± 3.2 mm)
LENGTH: $\pm 1/8"$ (± 3.2 mm) up to 12' (3.7 m)
SQUARENESS: $\pm 1/8"$ (3.2 mm) in 48" (1.2 m) of width
4. Product quality standards and tolerances for panel weight and thickness shall be as set forth in Crane Composites' Quality Control Procedures/Standards which are available on request.

CERTIFICATIONS

FRP does not support mold or mildew (per ASTM D3273 and ASTM D3274).

FABRICATING RECOMMENDATIONS

NOTE: Protect your eyes with goggles; cover your nose and mouth with a filter mask; cover exposed skin when cutting CCI panels.

HAND FABRICATING: Drilling—High speed drill bit (60° cutting angle, with 12°-15° clearance) or hole saw.

CUTTING: Sheet metal shears or circular saw with reinforced carborundum or carbide-tipped blade.

PRODUCTION FABRICATING: Use carbide-tipped tools. Straight cuts can be sheared (90° cutting edge with 0.002" [0.05 mm] clearance) or sawed. For irregular cuts, use die punch or band saw.

SDS: Prior to working with our products, see our most current SDS at cranecomposites.com/sds.html

STORAGE RECOMMENDATIONS

Store panels properly. While a single panel is engineered to withstand exposure to sunlight and the elements, a stack of panels will trap heat and moisture, causing internal clouding and/or yellowing in the panels. To avoid this irreversible effect, panels must be stored in a dry, shaded, well ventilated area. Skids should be elevated at one end by wood spacers. Failure to comply with recommended storage procedures will void the warranty on the panels.

CAUTIONS AND SAFETY WARNINGS

DO NOT WALK ON PANELS. Crane Composites panels are not intended to support the undistributed weight of workers. Roofing ladders or 1" x 12" planks, or equivalent means of protection must be used during any work on roofs. Provide fall protection in accordance with OSHA standard 29 CFR 1910 [see paragraph 1910.23(a)(4) AND (e)(8)]. Compliance with this regulation as well as any other local, state or federal safety requirements is the responsibility of the building owner, contractor and/or erector.

MAINTENANCE

Panels will provide a clean, aesthetically-pleasing finished installation. However, by nature, fiberglass reinforced plastic paneling may occasionally have small areas that are aesthetically unacceptable for use. Panels should be inspected on-site prior to installation. If any portion of material does not provide an acceptable appearance, Crane Composites should be notified at once. Upon verification of unacceptability, that portion of material will be replaced by Crane Composites. Crane Composites' sole responsibility is for the replacement of defective materials but not for labor or other handling or installation expenses.

We believe all information given is accurate, without guarantee. Since conditions of use are beyond our control, all risks are assumed by the user. Nothing herein shall be construed as a recommendation for uses which infringe on valid patents or as extending a license under valid patents. See our most current SDS at cranecomposites.com/sds.html prior to working with our products.

A global leading provider of resilient wall and ceiling coverings. Kemlite® was established in 1954 and the company changed names to Crane Composites in 2007. Crane Composites is headquartered in Channahon, IL and all our products are manufactured in the United States. We work with hundreds of distributors, ensuring our products are easily accessible and readily available to our customers.

The following are trademarks of Crane Composites, Inc. or a related company: SunStrong, Duralite, IsoTuff, Weatherglaze, Super 600, Crystalite, Glasbord, Kemlite, Surfaseal, Sequentia and Varietex

